CYCOLOY™ FR RESIN RCX7243

REGION ASIA

DESCRIPTION

CYCOLOY* RCX7243 is an impact modified PC blend containing 30% PCR content with non-brominated and non-chlorinated FR for thin-wall applications requiring excellent impact/flow balance performance.

TYPICAL PROPERTY VALUES

Revision 20241021

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	53	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	60	%	ASTM D638
Tensile Modulus, 5 mm/min	2400	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	100	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2350	MPa	ASTM D790
IMPACT [1]			
Izod Impact, notched, 23°C	690	J/m	ASTM D256
Izod Impact, notched, -30°C	130	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	57	J	ASTM D3763
Izod Impact, notched 80*10*3 +23°C	50	kJ/m²	ISO 180/1A
THERMAL [1]			
Vicat Softening Temp, Rate B/50	104	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	86	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	101	°C	ASTM D648
CTE, -40°C to 40°C, flow	7.5E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	7.5E-05	1/°C	ASTM E831
Relative Temp Index, Elec [2]	80	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	80	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	80	°C	UL 746B
PHYSICAL [1]			
Specific Gravity	1.19	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm [3]	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	19	g/10 min	ASTM D1238
Water Absorption, (23°C/saturated)	0.15	%	ISO 62-1
ELECTRICAL [1]			
Hot-Wire Ignition (HWI), PLC 2	≥3	mm	UL 746A
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E207780-102079922	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.75	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥0.6	mm	UL 94
UL Recognized, 94V-2 Flame Class Rating	≥0.4	mm	UL 94

© 2024 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
INJECTION MOLDING [4]			
Drying Temperature	80 – 90	°C	
Drying Time	2 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 300	°C	
Nozzle Temperature	250 – 300	°C	
Front - Zone 3 Temperature	250 – 300	°C	
Middle - Zone 2 Temperature	240 – 290	°C	
Rear - Zone 1 Temperature	230 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 85	°C	
Vent Depth	0.03 - 0.075	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.,The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2024 Copyright by SABIC. All rights reserved