CYCOLOY™ FR RESIN RCY6214

REGION ASIA

DESCRIPTION

CYCOLOY RCY6214 resin is an injection moldable PC/ABS blend with non-brominated and non-chlorinated flame retardant. It contains 35% post consumer recycle content with a UL-94 V0 rating @ 1.5 mm. Developed for wide variety of applications that require balanced flow and impact performance. Limited availability and restricted color only.

TYPICAL PROPERTY VALUES

Revision 20241021

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL [1]			
Tensile Stress, yld, Type I, 50 mm/min	60	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	47	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	40	%	ASTM D638
Tensile Modulus, 50 mm/min	2500	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	90	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2400	MPa	ASTM D790
IMPACT [1]			
Izod Impact, notched, 23°C	500	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	50	J	ASTM D3763
Izod Impact, notched 80*10*3 +23°C	51	kJ/m²	ISO 180/1A
THERMAL [1]			
Vicat Softening Temp, Rate B/50	100	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	85	°C	ASTM D648
HDT, 0.45 MPa, 6.4 mm, unannealed	101	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	92	°C	ASTM D648
CTE, -40°C to 60°C, flow	7.1E-05	1/°C	ASTM E831
CTE, -40°C to 60°C, xflow	7.2E-05	1/°C	ASTM E831
Relative Temp Index, Elec [2]	85	°C	UL 746B
Relative Temp Index, Mech w/impact [2]	85	°C	UL 746B
Relative Temp Index, Mech w/o impact [2]	85	°C	UL 746B
PHYSICAL [1]			
Specific Gravity	1.18	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.1	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm [3]	0.4 – 0.6	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm [3]	0.4 – 0.6	%	SABIC method
Melt Flow Rate, 260°C/2.16 kgf	21	g/10 min	ASTM D1238
ELECTRICAL [1]			
Hot-Wire Ignition (HWI), PLC 2	≥3	mm	UL 746A
FLAME CHARACTERISTICS [2]			
UL Yellow Card Link	E207780-100937373	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.5	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥1.2	mm	UL 94

© 2024 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94HB Flame Class Rating	≥0.3	mm	UL 94
INJECTION MOLDING [4]			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	8	Hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	245 – 275	°C	
Nozzle Temperature	245 – 275	°C	
Front - Zone 3 Temperature	245 – 275	°C	
Middle - Zone 2 Temperature	220 – 265	°C	
Rear - Zone 1 Temperature	220 – 255	°C	
Mold Temperature	60 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	30 – 80	%	
Vent Depth	0.038 – 0.076	mm	

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(3) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.,The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(4) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2024 Copyright by SABIC. All rights reserved