LEXAN™ HEALTHCARE RESIN HPS7

REGION EUROPE

DESCRIPTION

LEXAN™ HPS7 resin is a 5 MFR polycarbonate, MVR of 5. Mold release. Biocompatible (ISO10993 or USP Class VI) grade for medical devices and pharmaceutical applications. It is EtO, steam, e-beam and gamma sterilizable. Subject to SABIC healthcare management of change process.

TYPICAL PROPERTY VALUES

Revision 20250805

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	72	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6.5	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	125	%	ASTM D638
Tensile Modulus, 50 mm/min	2350	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	100	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2350	MPa	ASTM D790
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	SABIC method
Tensile Stress, yield, 50 mm/min	61	MPa	ISO 527
Tensile Stress, break, 50 mm/min	71	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	126	%	ISO 527
Tensile Modulus, 1 mm/min	2450	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
Ball Indentation Hardness, H358/30	95	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	935	J/m	ASTM D256
Izod Impact, notched, -30°C	785	J/m	ASTM D256
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	75	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	15	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	75	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	15	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	146	°C	ASTM D1525
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	145	°C	ISO 306
Vicat Softening Temp, Rate B/120	146	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	139	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	128	°C	ISO 75/Ae

© 2025 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	128	°C	ISO 75/Af
CTE, 23°C to 80°C, flow	7.0E-05	1/°C	ISO 11359-2
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Melt Flow Rate, 300°C/1.2 kgf	5	g/10 min	ASTM D1238
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Density	1.2	g/cm³	ISO 1183
Water Absorption, (23°C/saturated)	0.35	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	5	cm³/10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	88 – 90	%	ASTM D1003
Haze, 2.54 mm	<0.8	%	ASTM D1003
Refractive Index	1.586	-	ISO 489
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 330	°C	
Nozzle Temperature	305 – 325	°C	
Front - Zone 3 Temperature	310 – 330	°C	
Middle - Zone 2 Temperature	300 – 320	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	80 – 115	°C	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2025 Copyright by SABIC. All rights reserved